

ELBAFOOD PTFE 2

ELBAFOOD PTFE 2 is specially formulated Silicone grease prepared from a medium viscosity silicone fluid thickened with food grade PTFE. The grease is intended for applications where incidental food contact is possible.

Recommended Temperature Range: <-40°C to 260°C

Features:

ELBAFOOD PTFE 2 does not contain hazardous ingredients. FDA Compliance 21CFR 178.3570 Non Corrosive, Chemical Inert Hydrolytically Stable, release agent, O-ring lubricant. High chemical, oxidation, and radiation resistance, Odorless, non-toxic, non-melting.

Application:

Indirect Food Contact, Fire Extinguisher Valves, Vacuum / Pressure Systems, Auto Ignition, Plug Valves, Electrical Connections and Corrosion Protection.

TYPICAL PROPERTIES:	METHOD	RESULT
Base Fluid	Report	Silicone
Base Fluid Viscosity, 25°C	ASTM D445	350 cSt
Thickener	Report	PTFE
Color	Visual	White
Appearance	Visual	Smooth
P ₀	ASTM D217	214
P ₆₀	ASTM D217	217
Density, 25°C	CTM-2	1.32 g/cc
Oil Separation, 24h at 100°C	ASTM D6184	0.93%
Evaporation, 24h at 100°C	CTM-1	0.33%

Disclaimer:

Since we are unable to anticipate or control the conditions under which this information and our products may be used, we cannot guarantee the applicability of this information or suitability of our products in any specific application. Moreover, the products are sold without warranty, expressed or implied. Statements concerning the possible use of our products are not intended as recommendations to use our product in the infringement of any patent.

For Technical, Quality or Product Safety Questions Please Contact:

Elba Lubrication Inc., New York / United States of America
Phone + 1-631-759-1014
info@elba-lubes.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

ELBALUBES™ | Most Recent Change: 01.07.2022

