

ELBA EFMG SERIES

Global.....Lubrication Specialist.

ELBA EFMG Series grease is an aluminum complex thickened synthetic lubricating grease created specifically for the food service, beverage, and packaging industries. The aluminum complex thickener system provides excellent water resistance and a broad operating temperature range. A combination of newly developed additives and dependable HX1 additives provide excellent anti-wear/extreme pressure properties, oxidation resistance, and corrosion prevention. Special additives are employed to keep the grease in place between wash-down cycles which improves equipment and lubricant life in wet conditions. ELBA EFMG Series is NSF Registered and meets USDA 1998 (H1) guidelines (lubricants with incidental food contact).

ELBA EFMG is ideal for lubrication of production equipment in beverage canning operations, bottling operations, meat and poultry processing, dairy operations, fruit and vegetable processing, bakeries, and pharmaceutical plants.

	General Characteristics	General Characteristics	General Characteristics
NLGI Grade	0	1	2
Color	Off White to Yellow	Off White to Yellow	Off White to Yellow
Texture	Homogenous	Homogenous	Homogenous
Base Oil	Mineral Oil/PAO	Mineral Oil/PAO	Mineral Oil/PAO
Base Oil Properties			138 cSt
Viscosity @ 40°C cSt	138 cSt	138 cSt	17.5 cSt
Viscosity @ 100°C cS	17.5 cSt	17.5 cSt	140
Viscosity Index	140	140	Aluminum Complex
Thickener Type	Aluminum Complex	Aluminum Complex	.97
Density at 20°C (g/cm)	-	.95	-30°C-148°C (300°F
Service Temperature Range	-35°C-148°C (300°F)	-35°C-148°C (300°F)	270°C (518°F)
Drop Point	210°C (410°F)	250°C (482°F)	
Penetration			
Worked 60 dbl strokes	360	320	280
100,000 dbl strokes	-	350	308
Oil Separation	Less than 10%	Less than 7%	Less than 3%
4-Ball Wear ASTM D22	0.45 mm	0.45 mm	0.47 mm
4-Ball Load Wear Index	37.9	48.9	64.3
Last non-seizure Load	80 kg	100 kg	100 kg
Weld Load	250 kg	315 kg	400 kg
Corrosion Preventative			
Properties ASTM D 1743	-	Pass	Pass
Corrosion Preventative			
Properties EMCOR			
ASTM D 6138	0.0	0.0	0.0
Water Washout			
ASTM D 1264	4.5%	9%	3%
NSF Registered	Pending	H1	H1
Kosher Approved	Pending	Yes	Yes
CFIA Accepted	Pending	Pending	Yes

Shelf Life: Product shelf life is 3 years from the date of manufacture, after which the product should be recertified prior to use.

For Technical, Quality or Product Safety Questions Please Contact:

Elba Lubrication Inc., New York / United States of America Phone + 1-631-759-1014

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement hithir parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.



info@elba-lubes.com